



Paint Manufacturers

3 Pendrey Court, Woodridge, Qld 4114

Phone : (07) 3290 1444 Fax : (07) 3290 1555

Issued 1<sup>st</sup> August 2005

## PRODUCT DATA SHEET

---

### 844 CLEARLAC

<b>Description</b>	Clearlac is a high solids, single pack, clear lacquer specifically designed to give a superior finish to quality furniture.	
<b>Features</b>	<ul style="list-style-type: none"> <li>• High build</li> <li>• Improved holdout</li> <li>• Fast dry and through cure</li> <li>• Smooth appearance and soft feel</li> </ul>	<ul style="list-style-type: none"> <li>• Excellent abrasion and scuff resistance</li> <li>• High alcohol and stain resistance</li> </ul>
<b>Typical Uses</b>	Clear lac is designed for factory application as a topcoat for commercial furniture.	
<b>Application Data</b>	Gloss:	Matt, Satin, Semi-Gloss or Gloss
	Colour:	Clear
	Shelf Life @ 25°C:	6-12 months
	Thinner:	Lacquer Thinner
	Clean Up:	Lacquer Thinner or Multipurpose Thinner
	Spread Rate:	10-12 m <sup>2</sup> /lt less losses due to application method, conditions of application and surface characteristics
	Dry Times:	Dust Free: 10-15 minutes Touch Dry: 20-30 minutes Hard Dry: 3-4 hours
	Application:	May be applied by conventional spray, pressure pot, gravity feed, airless spray. To achieve maximum build do not thin, but it may be necessary to thin up to 10-25% with Lacquer Thinners depending on application equipment used.
	Container Sizes:	4 litre, 20 litre, 60 litre, 200 litre

**Application  
Summary**

Stir thoroughly until Clearlac is of uniform consistency.

Prepare surface by filling imperfections with timber putty. Sand smooth with 180-240 grade paper and remove sanding dust. Ensure that you sand in the direction of the grain.

Stain (if required) with 812 Quickwipe or 818 Easistain according to directions.

Apply one double header coat of 830 Clearseal or 838 Highseal to seal the timber surface. Very open grained timber may require a second seal coat. Refer to data sheet for application details.

Sand after one hour with 280-320 grade paper and remove dust.

Clearlac should be thinned only enough to flow freely through the application equipment. Apply one double header coat of 844. Sand after 1 hour and remove any sanding debris. Apply a second double header coat, if desired to finish off.

**Precautions**

Contains flammable solvents. Keep away from heat and flame. Provide adequate ventilation and wear protective clothing. Material Safety Data Sheet available on request.

**Classification**

UN 1263  
DG CLASS 3 PKG II  
HAZCHEM 3 [Y]E

---

Paintec Pty Ltd  
3 Pendrey Court  
Woodridge Qld 4114

Phone (07) 3290-1444  
Fax (07) 3290-1555

Due to differences in substrates, application methods and local conditions purchasers of this product must ensure that it is suitable for their specific application before using this product. While the information contained in the PDS is accurate to the best of our knowledge, Paintec Pty Ltd cannot guarantee that the information contained is wholly comprehensive. Subject to the provisions of the Trade Practices Act, the Company's liability in relation to defective product shall be limited to replacement or repair of the product or the supply of equivalent product.